

PRODUCT *Info*

DeoxIT® Grease

**Maximize
Mechanical & Electrical Performance!™**

M260 and L260 Greases

Manufactured in semi-solid form for use as a combination cleaning, deoxidizing, protecting and lubricating preparation. Greases protect against oxidation (galvanic corrosion) and are free of mineral acids, sulphurs, alkalis and other noxious components aggressive to metals. DeoxIT® Greases improve performance of electrical contacts and mechanical components that require precise lubrication.

DeoxIT® Grease Type M260 - Mineral-based preparation.

Excellent lubrication, good wear resistance, excellent oxidation (galvanic corrosion) protection and good dripping-point characteristics.

Operating temperatures: M260 Greases: -40°C to 260°C

DeoxIT® Grease Type L260 - Lithium-based preparation.

Good lubrication, excellent wear resistance, excellent pressure resistance, excellent oxidation (galvanic corrosion) protection, high dripping-point characteristics.

Operating temperatures: L260: -40°C to 260°C.

USES - Electrical:

Antenna connections, battery terminals, Buss bars, commutators, conductor rails, conductors, contactors, disconnects, drying & processing equipment, high amperage/high voltage applications, industrial electrical equipment (lifts, cranes, robotics, etc.), power tools, relays & switches (heavy duty, knife, step, rotary), etc.

USES - Mechanical:

Bearings (all types), doors (closures), drives (chain/sprockets), hatch closures, O-rings and seals, linear motion systems, plugs (threaded holes), rack & pinion assemblies, screw devices (jacks, rails), slide bushings, sliding parts, tracks/guides/rails, threaded closures, worm gears, etc.

DeoxIT® Products . . .

used by those who demand the best!

Boeing	General Electric	McIntosh Labs	Switchcraft
Daktronics	Hewlett-Packard	Motorola	Tektronix
Diebold Inc.	Honeywell	Nokia	Union Pacific
Dolby Laboratories	Intel	Philips Healthcare	Wayne-Dresser
Dover Elevator	John Deere	Rane Corp.	Xerox Corp.
Federal Express	Logitech	Roland	and many more!



GREASE TYPES:

DeoxIT® Type M260 Np, No particles
 DeoxIT® Type M260 Cp, Copper particles
 DeoxIT® Type L260 Np, No particles
 DeoxIT® Type L260 Cp, Copper particles
 DeoxIT® Type L260 Ap, Aluminum particles
 DeoxIT® Type L260 Qp, Quartz particles
 DeoxIT® Type L260 Gp, Graphite particles
 DeoxIT® Type L260 GQp, Graphite & Quartz
 DeoxIT® Type L260 Tp, Teflon

GREASE DESCRIPTIONS:

No particles: Maximum lubrication for relatively clean surfaces.

Copper particles: Copper particles assist in breaking up oxidation and corrosion. Copper is conductive.

Aluminum particles: Use when aluminum metals are involved. Use in areas that two contacts will not touch and possibly short.

Quartz particles: Quartz particles assist in breaking up oxidation and corrosion. Quartz is nonconductive.

Graphite particles: Graphite particles assist in heat stability and lubrication. Graphite is excellent for heat transfer.

Graphite and Quartz particles: Use when heat transfer, lubrication and assistance is needed in breaking up oxides and corrosion.

Teflon: For superior lubrication and protection of parts.



Home of the DeoxIT® family of
 Environmentally-Safer Contact Cleaners and
 Connector Enhancing Treatments
 Made in USA



Audio/Video



Computers



Automotive



Communications



Marine



Electrical



Energy



Photography



Security



Medical



Avionics

1. DeoxIT® Type M260Np, No particles, -40°C to 260°C

M260-N1	28 grams jar
M260-N50G	50 grams cartridge
M260-N8	226 grams jar
M260-N35	35 lb. (16kg) pail

2. DeoxIT® Type M260Cp, Copper particles, -40°C to 260°C

M260-C1	28 grams jar
M260-C50G	50 grams cartridge
M260-C8	226 grams jar
M260-C35	35 lb. (16kg) pail

3. DeoxIT® Type L260Np, No particles, -40°C to 260°C

L260-N2G	2 gram Squeeze Tube
L260-N1	28 grams jar
L260-N50G	50 grams cartridge
L260-N8	226 grams jar
L260-N35	35 lb. (16kg) pail

4. DeoxIT® Type L260Cp, Copper particles, -40°C to 260°C

L260-C1	28 grams jar
L260-C50G	50 grams cartridge
L260-C8	226 grams jar
L260-C35	35 lb. (16kg) pail

5. DeoxIT® Type L260Ap, Aluminum particles, -40°C to 260°C

L260-A1	28 grams jar
L260-A50G	50 grams cartridge
L260-A8	226 grams jar
L260-A35	35 lb. (16kg) pail

6. DeoxIT® Type L260Gp, Graphite particles, -40°C to 260°C

L260-G1	28 grams jar
L260-G50G	50 grams cartridge
L260-G8	226 grams jar
L260-G35	35 lb. (16kg) pail

7. DeoxIT® Type L260Qp, Quartz particles, -40°C to 260°C

L260-Q1	28 grams jar
L260-Q50G	50 grams cartridge
L260-Q8	226 grams jar
L260-Q35	35 lb. (16kg) pail

8. DeoxIT® Type L260GQp, Graphite /Quartz particles, -40°C to 260°C

L260-GQ1	28 grams jar
L260-GQ50G	50 grams cartridge
L260-GQ8	226 grams jar
L260-GQ35	35 lb. (16kg) pail

9. DeoxIT® Type L260Tp, Teflon particles, -40°C to 260°C

L260-T1	28 grams jar
L260-T50G	50 grams cartridge
L260-T8	226 grams jar
L260-T35	35 lb. (16kg) pail

COMPARISON CHART

Product	Heat Resistance	Water Resistance	Oxidation Resistance *	Oxidation Dissolving
DeoxIT® M260	Excellent	Good	Excellent	Good
DeoxIT® L260	Excellent	Excellent	Excellent	Good
Lithium	Good	Good	Fair	Poor
Lithium Complex	Excellent	Excellent	Fair	Poor
Complex	Excellent	Excellent	Fair	Poor
Bentone Clay	Excellent	Good	Good	Poor
Polyurea	Excellent	Excellent	Good	Poor

* Oxidation of lubricants can produce sludge, varnish, gum and acid.

TYPICAL PROPERTIES (Base material):

	TYPE:	
	M260	L260
Flow Point, min.	-30°C	-30°C
Viscosity @ 100°F, SUS	763	785
ASTM Dropping Point	260°C	285°C
Specific Gravity @ 20°C	1.85	1.87
Flash Point	300°C	300°C
¹ Lowest/Best Operating Temperature (general)	-30°C	-30°C
¹ Highest Operating Temperature (continuous duty)	200°C	200°C
Acid & Neutralization No. (mg KOH/g)	1.15	1.17
Saponification No. (mg KOH/g)	2.79	2.81
Electrical Conductivity (27°C)(10 ⁻¹² ohm ⁻¹ cm ⁻¹)	0.17	0.17
² Dielectric Constant E _r	2.75	2.81
Tan δ (10 ⁻⁴)		
² Dielectric Strength E _d (kV/cm)	54.6	45.9
² Insulation Resistance D (10 ⁻¹² ohm-cm)	5.7	5.9
	+50/-0.03	+50/-0.03
Oil Type	Mineral	Synthetic Blend
Soap Type	None	Lithium-12 Hydroxy
Soap %		9.52
ASTM - Penetration	280	295
NLGI	2	2
Deoxidizer	Yes	Yes
Oxidation Inhibitor	Yes	Yes
Corrosion Inhibitor	Yes	Yes
Texture	Buttery	Short Fiber
Color	Amber	Amber

¹ Temperatures are conservative values for reference only.² **NOTE:** All values are relative to an ambient temperature of 26 to 28°C (approx. 80°F). Dielectric strength value is a statistical average taken from 10 measurements. Voltage measurement taken with 0.5% accuracy. Tests conducted on base material only. Greases with particles may have different measurements.

All information and data contained in this literature is believed to be accurate, however, it should not be taken as definitive for all users. Users should thoroughly test advertised products in their application, and independently determine satisfactory results before use in large scale production or manufacturing processes. All information on the comparison chart on the front side of this literature we believe to be reliable and was, in part, provided by the manufacturer. Independent testing should be conducted to determine individual needs for each application.

VOC and RoHS Compliant**Product Information Sheet
C-LM260, 7/2014****CAIG Laboratories, Inc.**

12200 Thatcher Court, Poway, CA 92064 U.S.A.

P: 858/486-8388 | E: info@caig.com

WEB: www.caig.com | www.deoxit.com

**Made in USA**